



**KEEPS JOINTS AND DRILL CASING
TOGETHER TO SPEC!**

Two Part Thread Locking Compound

Spin Lock	Part 1	Part 2
Form	Paste	Liquid
Color	Gray	Maroon
NLGI	0-1	N/A
Penetration (ASTM-D-217)	330-365	N/A
Viscosity	N/A	400 cSt @25°C
Specific Gravity	1.4	1.0
Density (lb. /gal)	11.7	8.0
Flash Point	250°F (121°F)	>200°F (93°C)
Temperature Range	N/A	40°F to 450°F (4°C to 230°C)
Mixed Product Life	40 minutes @25°C	
Full Kit Cure Time	2 days @ 25°C	
Break Partial Cure	2800 PSI @ 4 hours cure time	
Break Full Cure	4000 PSI	
Friction Factor (API 7A 1)	0.9	

Do Not Use Spin Lock on Oxygen Service

