

# SPIN LOCK



## 2 PART THREAD LOCKING COMPOUND

### KEEP JOINTS & THREAD CASING TOGETHER TO SPEC!

SPIN LOCK	PART 1	PART 2
FORM	PASTE	LIQUID
COLOR	GRAY	MAROON
NLGI	0-1	N/A
PENETRATION (ASTM-D-217)	330-365	N/A
VISCOSITY	N/A	400 CST @250C
SPECIFIC GRAVITY	1.4	1.0
DENSITY (LB. /GAL)	11.7	8.0
FLASH POINT	250F (121F)	>200F (93C)
TEMPERATURE RANGE	N/A	40FTO 450(4C TO 230C)
MIXED PRODUCT LIFE		40 MINUTES @250C
FULL KIT CURE TIME		2 DAYS @ 250C
BREAK PARTIAL CURE		2800 PSI @ 4 HOURS CURE TIME
BREAK FULL CURE		4000 PSI
FRICTION FACTOR (API 7A 1)		0.9



Encore Industrial Products  
[www.encoreindustrial.com](http://www.encoreindustrial.com)  
 1-877-703-3044  
 PO BOX 300 BARKER, TX 77413

